



3706 W. Ferguson Rd., Fort Wayne, IN 46809
 Phone (260) 747-7411 Fax: (260) 747-7413

**LEECURE B-610
 BORON TRIFLUORIDE AMINE COMPLEX
 EPOXY CURING AGENT**

Description

LEECURE B-610 is the most reactive member of Leepoxy's proprietary liquid BF₃ epoxy curing agent family. When mixed with standard epoxy Bisphenol A resin, it provides a very fast tack-free cure at room temperature, assuming little or no heat sink effect. Its reactivity makes it attractive as a fast-set adhesive for bonding or tacking steel, aluminum, primed plastics, and a variety of other clean, dry materials. LEECURE B-610 can be dispensed via meter-mix equipment or dual cartridge guns utilizing small static mixers. It is appropriate for bonding applications requiring a small mass and high throughput

For higher performance applications, LEECURE B-610 can be used with epoxy novolac, and flexibilized epoxy resins. Cured systems offer exceptional chemical and heat resistance, tensile strength and electrical properties.

TYPICAL PROPERTIES	
Appearance	Brown liquid
Viscosity, 25°C, cps	14,000
Density, pounds/gallon	9.2
Shelf life, months	12

Handling and Mixing

Keep LEECURE B-610 containers tightly sealed at all times. Use of dry nitrogen is recommended to protect partial containers from moisture contamination. The epoxy resin, fillers, and any other ingredients to be mixed should be moisture-free as well. Avoid alkaline fillers such as calcium carbonate. Fillers such as silica, barytes, glass, graphite, clays, and others that have a pH of 7 or lower are recommended. Mix very thoroughly in a dry mix vessel. No special equipment is necessary, but entrapment of excessive air bubbles should be avoided. Exposure to humidity in the air should be minimized from the time of mix until the product is ultimately cured. Prolonged exposure to humidity may harm the reactivity, physical properties, and surface appearance of a LEECURE B-610 cured system.

TYPICAL HANDLING PROPERTIES	
Mix Ratio ¹ , phr	8 – 12
Gel time, 25°C, 11 g, seconds	20
Work Life, 25°C, static mixer, seconds	30
Cure Time, 25°C, 3/16 inch bead, min	3

¹ Mix ratio with Bisphenol A Resin (EEW=189)

Curing Conditions

Epoxy compounds containing LEECURE B-610 should be cured so as to control the effects of the exothermic reaction. The optimum time and temperature will depend on the particular formulation and the mass of compound. Longer cure schedules may be needed when curing thin sections or where the epoxy is adjacent to a mass of material that will act as a heat sink. The recommended minimum bondline cure temperature is 25°C. Generally, the higher the cure temperature, the better the heat resistance and physical properties of the cured systems.

Additives, modifiers, and diluents used in formulating epoxy compounds incorporating LEECURE B-610 may have a marked effect not only on the cure rate but also the final properties of the cured system. Diluents, fillers, and flexibilizers will generally increase pot life, gel time, and cure time.

TYPICAL PERFORMANCE	
Glass Transition Temperature, °C	116
Tensile Strength, psi	1,000
Tensile Elongation, %	4.0
Hardness, Shore D	90

The Information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material. Freedom to use any patent owned by Leepoxy Plastics, Inc. or others is not to be inferred from any statement contained herein